

SUPERARC® L-50®

Mild Steel, Copper Coated ■ AWS ER70S-3 & EM13K



KEY FEATURES

- Moderate levels of manganese and silicon for deoxidization of clean to light mill scale surfaces
- Copper coating provides superior arc-starting characteristics for long contact tip life
- Supports short-circuiting, globular, axial spray and pulsed spray transfer
- MicroGuard® Ultra provides superior feeding and arc stability

WELDING POSITIONS

All

SHIELDING GAS

100% CO₂
 75-95% Argon / Balance CO₂
 95-98% Argon / Balance O₂
 Flow Rate: 30-50 CFH

DIAMETERS / PACKAGING

Diameter in (mm)	33 lb (15 kg) Plastic Spool	33 lb (15 kg) Steel Spool	44 lb (20 kg) Steel Spool	44 lb (20 kg) Fiber Spool	60 lb (27.2 kg) Coil
0.030 (0.8)	ED032923	ED031407			
0.035 (0.9)	ED032924	ED031408	ED031914	ED021268, ED036624*	
0.045 (1.1)	ED032925	ED031409, ED036879*	ED031915	ED021270, ED034428*	
0.052 (1.3)			ED031916		ED011317
1/16 (1.6)					
Diameter in (mm)	60 lb (27.2 kg) Fiber Spool	500 lb (227 kg) Accu-Trak® Drum	500 lb (227 kg) Accu-Pak® Box	500 lb (227 kg) Infinity-Pak®	600 lb (272 kg) Speed-Feed® Drum
0.030 (0.8)		ED029223			
0.035 (0.9)	ED021269	ED021052	ED032899		
0.040 (1.0)					
0.045 (1.1)	ED021271	ED020526	ED032901	ED034535	
0.052 (1.3)	ED021273	ED020527	ED032902		
1/16 (1.6)	ED027274		ED032903		ED011316
Diameter in (mm)	900 lb (408 kg) Accu-Pak® Box	1000 lb (454 kg) Accu-Trak® Drum	1000 lb (454 kg) Accu-Pak® Box	1000 lb (454 kg) Precise-Trak® Reel	1000 lb (454 kg) Infinity-Pak®
0.030 (0.8)					
0.035 (0.9)	ED032842	ED028825		ED032379	
0.040 (1.0)			ED033292	ED032380	
0.045 (1.1)		ED028826	ED032844	ED031614	ED031930
0.052 (1.3)		ED029082	ED032845	ED031615	ED034464
1/16 (1.6)		ED029083	ED032846	ED033270	

*Buy America Product

WIRE COMPOSITION⁽¹⁾ – As Required per AWS A5.18

	%C	%Mn	%Si	%S	%P
Requirements – AWS ER70S-3	0.006-0.15	0.90-1.40	0.45-0.75	0.035 max	0.025 max
Typical Results ⁽³⁾	0.08-0.11	1.14-1.23	0.53-0.59	0.003-0.009	0.003-0.013
	%Cr	%Mo	%Ni	%V	%Cu (Total) ⁽⁴⁾
Requirements – AWS ER70S-3	0.15 max	0.15 max	0.15 max	0.03 max	0.50 max
Typical Results ⁽³⁾	≤ 0.04	≤ 0.02	≤ 0.03	< 0.01	0.15-0.25

⁽¹⁾Typical all weld metal. ⁽²⁾Measured with 0.2% offset. ⁽³⁾See test results disclaimer ⁽⁴⁾Copper due to any coating on the electrode plus the copper content of the filler metal itself, shall not exceed the stated 0.50% max.

CONFORMANCES

AWS A5.18:	ER70S-3
ASME SFA-A5.18:	ER70S-3
AWS A5.17:	EM13K
ABS:	3YSA
Lloyd's Register:	3YS H15
DNV Grade:	III YMS
CWB/CSA W48-06:	ER49S-3
EN ISO 14341-B:	G 49A 2 C S3
MIL-E-23765/1:	MIL-70S-3

TYPICAL APPLICATIONS

- Clean to light mill scale base material
- Pipeline and processing pipe
- Sheet metal to 380 - 485 MPa (55 - 70 ksi) yield strength material
- Pressure vessels
- Structural steel

MECHANICAL PROPERTIES⁽¹⁾ – As Required per AWS A5.18

	Yield Strength ⁽²⁾ MPa (ksi)	Tensile Strength MPa (ksi)	Elongation %	Charpy V-Notch - J (ft-lbf)	
				@ -18°C (0°F)	@ -29°C (-20°F)
Requirements - AWS ER70S-3 As-Welded with 100% CO ₂	400 (58) min	485 (70) min	22 min	27 (20) min	Not Specified
MIL-70S-3 per MIL-E-23765/1 As-Welded with CO ₂ and 98% Ar/2% O ₂	380-485 (55-70)	485 (70) min	22 min	Not Specified	Not Specified
Typical Results⁽³⁾ As-Welded with 100% CO ₂ Stress Relieved 1 hr. @ 621°C (1150°F)	415 (60) 365 (53)	515 (75) 475 (69)	26 34	95 (70) 118 (87)	88 (65) 100 (74)
As-Welded with 75% Ar/25% CO ₂ Stress Relieved 1 hr. @ 621°C (1150°F)	420 (61) 365 (53)	525 (76) 490 (71)	28 33	106 (78) 165 (122)	102 (75) 163 (120)
As-Welded with 90% Ar/10% CO ₂ Stress Relieved 1 hr. @ 621°C (1150°F)	450 (65) 365 (53)	545 (79) 485 (70)	30 35	142 (105) –	122 (90) 214 (158)
As-Welded with 98% Ar/2% O ₂ Stress Relieved 1 hr. @ 621°C (1150°F)	425 (62) 350 (51)	540 (78) 475 (69)	27 33	108 (80) –	95 (70) 339 (250)

TYPICAL OPERATING PROCEDURES

Diameter, Polarity Shielding Gas	CTWD ⁽⁵⁾ mm (in)	Wire Feed Speed m/min (in/min)	Voltage (volts)	Approx. Current (amps)	Melt-Off Rate kg/hr (lb/hr)
0.030 in (0.8 mm), DC+					
Short Circuit Transfer 100% CO ₂	9-12 (3/8-1/2)	1.9 (75)	17	35	0.4 (0.9)
		3.8 (150)	18	70	0.8 (1.8)
		7.6 (300)	22	130	1.6 (3.6)
0.035 in (0.9 mm), DC+					
Short Circuit Transfer 100% CO ₂ ⁽⁶⁾	9-12 (3/8-1/2)	2.5 (100)	18	80	0.7 (1.6)
		3.8 (150)	19	120	1.1 (2.4)
		6.4 (250)	22	175	1.8 (4.0)
Spray Transfer 90% Ar/10% CO ₂	12-19 (1/2-3/4)	9.5 (375)	23	195	2.7 (6.0)
		12.7 (500)	29	230	3.6 (8.0)
		15.2 (600)	30	275	4.4 (9.6)
0.045 in (1.1 mm), DC+					
Short Circuit Transfer 100% CO ₂ ⁽⁶⁾	12-19 (1/2-3/4)	3.2 (125)	19	145	1.5 (3.4)
		3.8 (150)	20	165	1.8 (4.0)
		5.1 (200)	21	200	2.5 (5.4)
Spray Transfer 90% Ar/10% CO ₂	12-19 (1/2-3/4)	8.9 (350)	27	285	4.2 (9.2)
		12.1 (475)	30	335	5.7 (12.5)
		12.7 (500)	30	340	6.0 (13.2)
0.052 in (1.3 mm), DC+					
Spray Transfer 90% Ar/10% CO ₂	12-19 (1/2-3/4)	7.6 (300)	30	300	4.8 (10.6)
		8.1 (320)	30	320	5.2 (11.5)
		12.3 (485)	32	430	7.8 (17.1)
1/16 in (1.6 mm), DC+					
Spray Transfer 90% Ar/10% CO ₂	12-25 (1/2-1)	5.3 (210)	25	325	4.8 (10.7)
		6.0 (235)	27	350	5.4 (12.0)
		7.4 (290)	28	430	6.7 (14.8)

⁽¹⁾Typical all weld metal. ⁽²⁾Measured with 0.2% offset. ⁽³⁾See test results disclaimer ⁽⁴⁾Copper due to any coating on the electrode plus the copper content of the filler metal itself; shall not exceed the stated 0.50% max.

⁽⁵⁾CTWD (Contact Tip to Work Distance). Subtract 1/4 in (6.4 mm) to calculate Electrical Stickout. ⁽⁶⁾Procedures in these areas are procedures for short circuiting mode using 100% CO₂. When using 75% Argon, 25% CO₂, for short circuit transfer, reduce voltage by 1 to 2 volts.

Material Safety Data Sheets (MSDS) and Certificates of Conformance are available on our website at www.lincolnelectric.com

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

CUSTOMER ASSISTANCE POLICY

The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or advice about their use of our products. Our employees respond to inquiries to the best of their ability based on information provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or advice. Moreover, the provision of such information or advice does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or advice, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose is specifically disclaimed.

Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

Subject to Change – This information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.com for any updated information.